

Data Sheet

Premium Vinyl Siding
ProSpan[®] Soffit


Product Test Data

HOMEX[®] Vinyl Siding meets or exceeds all industry standards per ASTM D3679.

Siding Thickness	038" ± .001"
Specific Gravity	1.45
Tensile Strength (PSI)	7,154
Tensile Modulus (PSI)	416,900
IZOD Impact Strength @ 32°F ..	Passes per ASTM D3679
Heat Deflection Temp. @ 264 PSI	169°F
Coefficient of Linear Expansion	3.30 x 10 ⁻⁵
Warpage	0.00"
Heat Shrinkage	0.24%
Impact Resistance	Passes per ASTM D3679
Surface Distortion @ 140°F	0
Flame Spread Index	10
Fire Rating	Class A
Smoke Developed	395
Fuel Contribution	0
Average Time Of Burning	Self extinguished
Average Extent Of Burning	2.379mm
Weathering	Passes per ASTM D3679




Home Innovation
NGBS GREEN CERTIFIED™




10" Vinyl Soffit Solid 32US10SD02

Length 12' - 0" | 20 Panels/Carton | 2 Sq./Carton
15 Ctns./Crate | Carton Weight: 75.73 lbs.




10" Vinyl Soffit Vented 32US10VT02

Length 12' - 0" | 20 Panels/Carton | 2 Sq./Carton
15 Ctns./Crate | Carton Weight: 75.57 lbs.
Sq. in. Vent Area Per L.F.: 3.8




12" Vinyl Soffit Center Vent 332US12CV02

Length 12' - 0" | 16 Panels/Carton | 2 Sq./Carton
12 Ctns./Crate | Carton Weight: 71.50 lbs.
Sq. in. Vent Area Per L.F.: 1.3




12" Vinyl Soffit Solid 32US12SD02

Length 12' - 0" | 16 Panels/Carton | 192 Sq. Ft./Carton
12 Ctns./Crate | Carton Weight: 71.92 lbs.



12" Vinyl Soffit Vented 32US12VT02

Length 12' - 0" | 16 Panels/Carton | 192 Sq. Ft./Carton
12 Ctns./Crate | Carton Weight: 70.66 lbs.
Sq. in. Vent Area Per L.F.: 4.0



12" Vinyl Soffit Basket Weave Vented 32US12BW02

Length 12' - 0" | 16 Panels/Carton | 192 Sq. Ft. /Carton
12 Ctns./Crate | Carton Weight: 72.13 lbs.
Sq. in. Vent Area Per L.F.: 14.7