


Data Sheet

Oak Harbor® Vinyl Siding

Signature Style




Brushed Cedar Woodgrain Finish



Double 4" 26D4__

Length 12' - 6" | 24 Panels/Ctn. | 2 Sq./Ctn. | Ctn. Weight: 92.55 lbs.




Dutchlap 5" 26DL5__

Length 12' - 0" | 20 Panels/Ctn. | 2 Sq./Ctn. | Ctn. Weight: 87.26 lbs.


Color # | Color

				SeaSide Collection	
02 White Birch	43 Pebble Clay	51 Topaz	82 Meadow	23 Coastal Sky	
11 Classic Sand	44 Harbor Stone	52 Java	85 Keystone	24 Providence Yellow	
17 Warm Sandalwood	46 Basket Beige	61 Artisan Clay	86 Nutmeg	25 Sunset Peach	
22 Sunny Maize	47 Slate Blue	79 Seagrass		48 Concord Green	
41 Soft Willow	49 Graphite Grey	80 Twilight			



Double 5" 26D5__

Length 12' - 0" | 20 Panels/Ctn. | 2 Sq./Ctn. | Ctn. Weight: 87.05 lbs.



Dutchlap 4.5" 26DL45__

Length 12' - 1" | 22 Panels/Ctn. | 2 Sq./Ctn. | Ctn. Weight: 89.05 lbs.

Color # | Color

02 White Birch	43 Pebble Clay	51 Topaz	82 Meadow
11 Classic Sand	44 Harbor Stone	52 Java	85 Keystone
17 Warm Sandalwood	46 Basket Beige	61 Artisan Clay	86 Nutmeg
22 Sunny Maize	47 Slate Blue	79 Seagrass	
41 Soft Willow	49 Graphite Grey	80 Twilight	

Oak Harbor® Vinyl Siding w/Reinforced Nail Hem

RMC® Vinyl Siding meets or exceeds all industry standards per ASTM D3679.

Product Test Data

Siding Thickness..... .042" ± .001"	Flame Spread Index.....10
Specific Gravity.....1.45	Fire Rating Class A
Tensile Strength (PSI).....7,154	Smoke Developed.....395
Tensile Modulus (PSI).....416,900	Fuel Contribution.....0
IZOD Impact Strength @ 32°F.....Passes per ASTM D3679	Average Time Of Burning.....Self extinguished
Heat Deflection Temp. @ 264 PSI.....169°F	Average Extent Of Burning.....2.379 mm
Coefficient of Linear Expansion.....3.30 x 10 ⁻⁵	Weathering.....Passes per ASTM D3679
Warpage.....0.00"	Windload Rating*193 MPH
Heat Shrinkage.....0.3%	*(Wind Velocity based on IBC)
Surface Distortion @ 140°F.....0	Impact Resistance.....Passes per ASTM D3679