


Data Sheet

Spiegel Grove® Vinyl Siding

Classic Character




Brushed Cedar Woodgrain Finish




Double 4" 20D4__

Length 12' - 6" | 24 Panels/Ctn. | 2 Sq./Ctn. | 20 Ctns./Crate | Ctn. Weight: 87.08 lbs.



Dutchlap 4.5" 20DL45__

Length 12' - 1" | 22 Panels/Ctn. | 2 Sq./Ctn. | 16 Ctns./Crate | Ctn. Weight: 83.99 lbs.




Dutchlap 5" 20DL5__

Length 12' - 0" | 20 Panels/Ctn. | 2 Sq./Ctn. | 14 Ctns./Crate | Ctn. Weight: 82.26 lbs.

Color # | Color _____

02 White Birch	26 Summer Wheat	46 Basket Beige	61 Artisan Clay
11 Classic Sand	41 Soft Willow	47 Slate Blue	79 Seagrass
17 Warm Sandalwood	43 Pebble Clay	49 Graphite Grey	82 Meadow
22 Sunny Maize	44 Harbor Stone	52 Java	86 Nutmeg



Double 5" 20D5__

Length 12' - 0" | 20 Panels/Ctn. | 2 Sq./Ctn. | 15 Ctns./Crate | Ctn. Weight: 82.87 lbs.

Color # | Color _____

02 White Birch	41 Soft Willow	46 Basket Beige	82 Meadow
17 Warm Sandalwood	43 Pebble Clay	47 Slate Blue	86 Nutmeg
22 Sunny Maize	44 Harbor Stone	79 Seagrass	

Data Sheet

Spiegel Grove® Vinyl Siding


Classic Character



Brushed Cedar Woodgrain Finish

T3.3" 20T333__

Length 12' - 0" | 20 Panels/Ctn. | 2 Sq./Ctn. | 15 Ctns./Crate | Ctn. Weight: 83.98 lbs.



Color # | Color _____

- | | |
|---------------------------|------------------------|
| 02 White Birch | 44 Harbor Stone |
| 17 Warm Sandalwood | 46 Basket Beige |
| 22 Sunny Maize | 82 Meadow |
| 43 Pebble Clay | 86 Nutmeg |

Spiegel Grove® Vinyl Siding w/Reinforced Nail Hem

RMC® Vinyl Siding meets or exceeds all industry standards per ASTM D3679.

Product Test Data

Siding Thickness.....	040" ± .001"	Surface Distortion @ 140°F.....	0
Specific Gravity.....	1.45	Flame Spread Index.....	10
Tensile Strength (PSI).....	7,154	Fire Rating	Class A
Tensile Modulus (PSI).....	416,900	Smoke Developed.....	.395
IZOD Impact Strength @ 32°F.....	Passes per ASTM D3679	Fuel Contribution.....	0
Heat Deflection Temp. @ 264 PSI.....	169°F	Average Time Of Burning.....	Self extinguished
Coefficient of Linear Expansion.....	3.30 x 10 ⁻⁵	Average Extent Of Burning.....	2.379 mm
Warpage.....	0.00"	Weathering.....	Passes per ASTM D3679
Heat Shrinkage.....	0.3%	Windload Rating*	193 MPH
		*(Wind Velocity based on IBC)	
		Impact Resistance.....	Passes per ASTM D3679