

Data Sheet Universal Soffit

Value Performance




Item / Image

Description / Color


Item / Image

Description / Color




32US10SD02

**10" Vinyl Soffit / 02
White Birch**
Brushed Finish
Length 12' - 0"
20 Panels/Carton - Solid
2 Sq. / Carton
Carton Weight: 75.73 lbs.




32US10VT02

**10" Vinyl Soffit Vented / 02
White Birch**
Brushed Finish
Length 12' - 0"
20 Panels/Carton - Full Vent
2 Sq. / Carton
Carton Weight: 75.57 lbs.
Sq. In. Vent Area Per L.F.: 3.8




32US12SD02

**12" Vinyl Soffit / 02
White Birch**
Brushed Finish
Length 12' - 0"
16 Panels/Carton - Solid
192 Sq. Ft. / Carton
Carton Weight: 71.92 lbs.




32US12VT02

**12" Vinyl Soffit Vented / 02
White Birch**
Brushed Finish
Length 12' - 0"
16 Panels/Carton - Full Vent
192 Sq. Ft. / Carton
Carton Weight: 70.66 lbs.
Sq. In. Vent Area Per L.F.: 4.0



32US12CV02

**12" Vinyl Soffit / 02
White Birch**
Center Vented
Brushed Finish
Length 12' - 0"
16 Panels/Carton - Center Vent
192 Sq. Ft. / Carton
Carton Weight: 71.50 lbs.
Sq. In. Vent Area Per L.F.: 1.3



32US12BW02

**12" Vinyl Soffit / 02
White Birch**
Basket Weave Vented
Brushed Finish
Length 12' - 0"
16 Panels/Carton
192 Sq. Ft. / Carton
Carton Weight: 72.13 lbs.
Sq. In. Vent Area Per L.F.: 14.7

Universal Vinyl Soffit

RMC® Siding Vinyl Siding meets or exceeds all industry standards per ASTM D3679.

Product Test Data

Soffit Thickness.....038" ± .001"
Specific Gravity.....1.45
Tensile Strength (PSI).....7,154
Tensile Modulus (PSI).....416,900
IZOD Impact Strength @ 32°F.....Passes per ASTM D3679
Heat Deflection Temp. @ 264 PSI.....169°F
Coefficient of Linear Expansion.....3.30 x 10⁻⁵
Warpage.....0.00"
Heat Shrinkage.....0.3%
Impact Resistance..... Passes per ASTM D3679

Surface Distortion @ 140°F.....0
Fire RatingClass A
Flame Spread Index.....10
Smoke Developed.....395
Fuel Contribution.....0
Average Time Of Burning.....Self extinguished
Average Extent Of Burning.....2.379 mm
Weathering..... Passes per ASTM D3679
Impact Resistance..... Passes per ASTM D3679
Windload Rating*..... 162 MPH
(*Wind Velocity based in IBC)



Style Crest®, Inc.
2450 Enterprise St.
Fremont, Ohio 43420

Made in the U.S.A. by America's dedicated workforce.
Printed in the U.S.A.
Specifications are subject to change without notice



Home Innovation
NGBS GREEN CERTIFIED™